

AD-A269 680 ON PAGE

Form Approved
OMB No 0704-0188Pu
ses
col

estimated to average 1 hour per response, including the time for reviewing instructions, data needed, and completing and reviewing the collection of information. Send comments on this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0740-0188), Washington DC 20503.

1. AGENCY USE ONLY (LEAVE BLANK)		2. REPORT DATE June 1993		3. REPORT TYPE AND DTAES COVERED Extended abstract	
4. TITLE AND SUBTITLE Process Relationship as Influenced by Carbonization Rate				5. FUNDING NUMBERS C: PE: PR: 2864 TA: 00T7	
6. AUTHOR(S) Kristen M. Kliner, David P. Anderson, and Timothy D. Naughton*					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) *Phillips Laboratory OL-AC PL/VTSC 3 Antares Road Space and Missiles Technology Directorate Edwards AFB CA 93524-7400				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSORING/MONITORING AGENCY REPORT NUMBER 93-21728 	
11. SUPPLEMENTARY NOTES K.M. Kliner from Wright-Patterson AFB OH; D.P. Anderson from University of Dayton Res Inst COSATI CODE(S): 2201, 2202, 2108					
12a. DISTRIBUTION/AVAILABILITY STATEMENT Available in Proceedings of the Carbon Conference held June 1993 in Buffalo, New York APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED				12b. DISTRIBUTION CODE	
13. ABSTRACT (MAXIMUM 200 WORDS) Extended abstract continued on next page INTRODUCTION <p>The typical process cycle for a carbon-carbon composite begins with an organic matrix impregnated fibrous preform cured according to conventional composite practices (e.g., lay-up, bagging and autoclave cure; hot pressing; etc.). This cured composite is then subjected to a pyrolysis cycle in the absence of oxygen which results in the carbonization of the matrix. Carbonization cycles are carried out to temperatures of 650-800°C for several hours or even days. During these cycles as much as 50% of the matrix mix can be volatilized with simultaneous shrinkage and microcracking. The resultant porous, low density carbonaceous solid is usually densified by additional matrix impregnation and heat treatment steps.</p> <p>The extreme length of the carbonization process is due to the heating cycle development methodology. The development of the material properties was not understood, so to keep catastrophic defects from occurring, the heating cycle was made very slow. To intelligently control the process the materials process/property relationship must be understood. In this study the relationship between heating rate and physical development of the carbonization of a phenolic preform was investigated.</p> EXPERIMENTAL <p>Eight ply, 30.5cm x 20.3cm (12" x 8") laminates, warp aligned and [0/45/90-45]₂ of Hercules UHM fiber and a phenolic resin¹ were autoclave cured to 177°C (350°F). The phenolic composites were cured to a void-free ("non-porous") microstructure, where porosity was distributed through the fiber tows and resin. the cured resins were weighed and ultrasonically c-scanned with dimensional and density measurements taken.</p>					
14. SUBJECT TERMS Composites, Carbon-Carbon, Temperature				15. NUMBER OF PAGES	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified		18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified		19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	
				20. LIMITATION OF ABSTRACT SAR	

NSN 7540-010280-5500

i/ii

Standard Form 298 (Rev 2-89)
Prescribed by ANSI Std Z39-18
298-102

Block 13 continued

The various structured phenolic preforms were then carbonized to 850°C (1562°F) at programmed furnace heating rates of 2, 5, 10, and 50 °C/min. The composites were cut in half; half for testing, half for continued processing. The processing was completed with a graphitization cycle, followed by chemical vapor deposition (CVD), graphitization, then CVD.

Testing of the carbonized and densified composites consisted of weight and dimensional measurements (used to calculate density) and microscopy (fluorescent and bright field) evaluation. These test results showed the influence of the carbonization heating rate, lay-up geometry, and/or phenolic microstructure on the carbon-carbon material development.

RESULTS AND DISCUSSION

The results from each test were analyzed to determine the effects of the carbonization heating rate, lay-up geometry, and/or phenolic microstructure had on the as carbonized and fully-densified composite microstructure.

When the thickness change from the cured phenolic to the carbonized state was analyzed, it was seen that the only effect was the "non-porous" thicknesses did not decrease as much as the "porous" composite thickness. The fully densified composite thickness any effect from the carbonization heating rate, lay-up geometry, and/or phenolic microstructure. All thickness data are shown in Table 1.

The weight change seen in Table 2, was measured through each process stage. Through the first carbonization cycle the weight change was greatly effected by the different phenolic microstructures, in which the porous phenolic composites lost less weight than the non-porous microstructure. The heating rate and ply construction did not influence the weight change. During densification, the composites carbonized at the different rates showed similar weight increases. however, the weight increase was different for the composites with the different phenolic microstructures and lay-up constructions. The "porous", quasi-isotropic composites gained more weight than the "non-porous", warp-aligned composites.

Density measurements, shown in Table 3, were taken to show the porosity changes during the process. As expected, the density decreased from the cured to the carbonized state, however, there was no density differences seen from the tested composite variables. The results show each composite density increased through the densification cycle to approximately the same final values. The different phenolic microstructures, lay-up geometry, and heating rates did effect the change in density through the various processes.

A microscopy analysis of samples showed the microstructurally "porous" composites contained more porosity than the microstructurally "non-porous" composite, even after the materials had been densified to the final state. The porosity in the "porous" densified samples could be characterized as frequent but larger than the "non-porous" samples. The quasi-isotropic construction seemed to contain less areas of porosity than the warp-aligned construction.

CONCLUSIONS

With the composite configuration used for these experiments, heating rate did not significantly alter any of the microstructural characteristics. The density, weight change, and thickness were not effected as the composites were carbonized at the faster rates.

The difference in the initial microstructure did provide some differences in the composite microstructure. During the carbonization cycle, the phenolic composites cured to a "non-porous" microstructure, lost more weight yet had less thickness decrease than the "porous" phenolic microstructures. The difference in weight loss was due to the different resin contents and resin distribution in the cured composites. When the composites were densified, the "non-porous" microstructures gained less weight.

Before densification, there was no significant difference between the quasi-isotropic and the warp-aligned composites. After densification, the quasi-isotropic geometry gained more weight and contained less porosity than the warp-aligned composites. Apparently, the fiber weave was spaced to allow the maximum diffusion of the densification gases.

REFERENCES

W. Phillips, et al., "Carbon-Carbon Composites Technology : Phase I Report", PL-TR-91-3061 (1991) Available NTIS, Springfield VA 22151.

ACKNOWLEDGEMENTS

This is a joint effort involving many individuals at the Phillips Laboratory/Space and Missiles Directorate and the Wright Laboratory/Materials Directorate in-house and on-site programs.

2 = 2°C/hour carbonization rate

5 = 5°C/hour carbonization rate

10 = 10°C/hour carbonization rate

50 = 50°C/hour carbonization rate

W + Warp Aligned Lay-up

Q = Quasi-Isotropic Lay-up

P = Porous phenolic microstructure

N = Non-porous phenolic microstructure

DTIC QUALITY INSPECTED 3

Accession For	
NTIS CRAWI	X
DTIC TAB	
Unannounced	
Justification	
By	
Distribution /	
Availability	
Dist	Avail and/or Spec
A-1	

Table 1. Thickness Measurements through the Process Stages		
Composite ID	1st Carbed C-C Avg Thickness Change (%)	Densified C-C Avg Thickness Change (%)
2 WN	-5.1	-0.7
2 WP	-3.4	1.2
2 QP	-3.6	4.5
2 QN	-5.3	2.7
5 WN	-5.7	-3.0
5 WP	-4.2	0.8
5 QP	-3.0	1.0
5 QN	-7.7	4.8
10 WN	-4.2	-2.9
10 WP	-3.3	0.0
10 QP	-2.9	0.7
10 QN	-5.5	5.8
50 WN	-3.4	-2.7
50 WP	-3.3	1.9
50 QP	-3.6	2.4
50 QN	-6.2	-1.0

Table 2. Weight Change Data through the Process Changes		
Composite ID	1st Carbed C-C Avg Thickness Change (%)	Densified C-C Avg Thickness Change (%)
2 WN	-26.1	15.9
2 WP	-24.0	23.9
2 QP	-28.5	28.4
2 QN	-27.1	24.7
5 WN	-15.6	16.4
5 WP	-14.1	22.4
5 QP	-17.3	27.6
5 QN	-16.3	25.3
10 WN	-14.8	15.4
10 WP	-15.9	20.6
10 QP	-17.2	28.2
10 QN	-16.5	25.4
50 WN	-15.8	21.2
50 WP	-15.1	15.9
50 QP	-16.9	23.1
50 QN	-17.0	28.7

Table 3. Density Measurements through the Process Stages				
Composite ID	1st Carbed C-C		Densified C-C	
	Avg density	Std density	Avg Density	Std density
2 WN	1.37	0.01	1.57	0.03
2 WP	1.34	0.03	1.57	0.02
2 QP	1.25	0.01	1.53	0.02
2 QN	1.29	0.01	1.53	0.03
5 WN	1.37	0.02	1.56	0.03
5 WP	1.32	0.02	1.56	0.01
5 QP	1.25	0.01	1.51	0.04
5 QN	1.30	0.01	1.51	0.06
10 WN	1.39	0.01	1.58	0.02
10 WP	1.34	0.01	1.54	0.03
10 QP	1.25	0.02	1.51	0.03
10 QN	1.29	0.02	1.53	0.02
50 WN	1.38	0.03	1.61	0.03
50 WP	1.30	0.01	1.56	0.01
50 QP	1.25	0.01	1.52	0.04
50 QN	1.30	0.02	1.52	0.01